

American Nuclear Society

**nuclear analysis and design
of concrete radiation shielding
for nuclear power plants**


an American National Standard

REAFFIRMED

August 4, 2016

ANSI/ANS-6.4-2006; R2016

This standard has been reviewed and reaffirmed with the recognition that it may reference other standards and documents that may have been superseded or withdrawn. The requirements of this document will be met by using the version of the standards and documents referenced herein. It is the responsibility of the user to review each of the references and to determine whether the use of the original references or more recent versions is appropriate for the facility. Variations from the standards and documents referenced in this standard should be evaluated and documented. This standard does not necessarily reflect recent industry initiatives for risk informed decision-making or a graded approach to quality assurance. Users should consider the use of these industry initiatives in the application of this standard.



published by the
American Nuclear Society
555 North Kensington Avenue
La Grange Park, Illinois 60526 USA

**American National Standard
Nuclear Analysis and Design of Concrete
Radiation Shielding for Nuclear Power Plants**

Secretariat
American Nuclear Society

Prepared by the
**American Nuclear Society
Standards Committee
Working Group ANS-6.4**

Published by the
**American Nuclear Society
555 North Kensington Avenue
La Grange Park, Illinois 60526 USA**

Approved September 29, 2006
by the
American National Standards Institute, Inc.

American National Standard

Designation of this document as an American National Standard attests that the principles of openness and due process have been followed in the approval procedure and that a consensus of those directly and materially affected by the standard has been achieved.

This standard was developed under procedures of the Standards Committee of the American Nuclear Society; these procedures are accredited by the American National Standards Institute, Inc., as meeting the criteria for American National Standards. The consensus committee that approved the standard was balanced to ensure that competent, concerned, and varied interests have had an opportunity to participate.

An American National Standard is intended to aid industry, consumers, governmental agencies, and general interest groups. Its use is entirely voluntary. The existence of an American National Standard, in and of itself, does not preclude anyone from manufacturing, marketing, purchasing, or using products, processes, or procedures not conforming to the standard.

By publication of this standard, the American Nuclear Society does not insure anyone utilizing the standard against liability allegedly arising from or after its use. The content of this standard reflects acceptable practice at the time of its approval and publication. Changes, if any, occurring through developments in the state of the art, may be considered at the time that the standard is subjected to periodic review. It may be reaffirmed, revised, or withdrawn at any time in accordance with established procedures. Users of this standard are cautioned to determine the validity of copies in their possession and to establish that they are of the latest issue.

The American Nuclear Society accepts no responsibility for interpretations of this standard made by any individual or by any ad hoc group of individuals. Requests for interpretation should be sent to the Standards Department at Society Headquarters. Action will be taken to provide appropriate response in accordance with established procedures that ensure consensus on the interpretation.

Comments on this standard are encouraged and should be sent to Society Headquarters.

Published by

**American Nuclear Society
555 North Kensington Avenue
La Grange Park, Illinois 60526 USA**

Copyright © 2006 by American Nuclear Society. All rights reserved.

Any part of this standard may be quoted. Credit lines should read "Extracted from American National Standard ANSI/ANS-6.4-2006 with permission of the publisher, the American Nuclear Society." Reproduction prohibited under copyright convention unless written permission is granted by the American Nuclear Society.

Printed in the United States of America

Foreword

(This Foreword is not a part of American National Standard “Nuclear Analysis and Design of Concrete Radiation Shielding for Nuclear Power Plants,” ANSI/ANS-6.4-2006.)

The need for this standard was identified in mid-1972 by D. K. Trubey, then chairman of Subcommittee ANS-6, Radiation Protection and Shielding. The then-existing standard, ANSI N101.6-1972, “Concrete Radiation Shields,” provided excellent guidance on the construction of concrete radiation shielding structures but contained almost no information on shielding effectiveness or analysis. This standard was first issued as ANSI/ANS-6.4-1977 (N403).

After ANSI/ANS-6.4-1977 was issued, two significant events occurred that led to the decision to revise the standard: ANSI N101.6-1972 was withdrawn by ANSI, and the American Concrete Institute (ACI) issued its standard ACI 349-80, “Code Requirements for Nuclear Safety Related Concrete Structures,” as well as the Commentary ACI 349R-80, which provided updated requirements with regard to the construction aspects of concrete shielding structures. The withdrawal of ANSI N101.6-1972; the guidance provided by ACI 349-80; and advances in the evolution of shielding methods, data, and applications led to the revision, ANSI/ANS-6.4-1985.

Since that revision effort, advances in buildup factors prompted the revision ANSI/ANS-6.4-1997. Other advances, particularly with respect to transmission and reflection of gamma rays and neutrons by concrete slabs, prompted the current revision, ANSI/ANS-6.4-2006.

This revised standard is meant to be a “guide to good practice” in the area of concrete shielding analysis and design. Recommendations are given where possible, but more often the choice of analytical methods must be left to the discretion of the shielding engineer as appropriate to the particular job, whether it be a conceptual design or final construction drawing.

This standard was revised by Working Group ANS-6.4 of the American Nuclear Society, which had the following members at the time it prepared and approved this standard:

R. E. Faw (Chair), *Individual*

R. J. Donahue, *Lawrence Berkeley National Laboratory*

C. C. Graham, *AmerenUE Callaway Plant*

S. J. Haynes, *Sandia National Laboratories*

T. M. Lloyd, *EnergySolutions*

J. D. Olson, *Black & Veatch Corporation*

J. K. Shultis, *Kansas State University*

R. W. Roussin, *Individual*

J. K. Warkentin, *Individual*

Subcommittee ANS-6, Radiation Protection and Shielding, had the following membership at the time of its approval of this standard:

W. C. Hopkins (Chair), *Individual*

F. A. Alpan, *Westinghouse Electric Company*

J. Tanner, *Pacific Northwest National Laboratory*

R. E. Faw, *Individual*

J. C. Wagner, *Oak Ridge National Laboratory*

R. M. Westfall, *Oak Ridge National Laboratory*

T. M. Raby, *National Institute of Standards and Technology*

N. Hertel, *Georgia Institute of Technology*

Consensus Committee N-17, Research Reactors, Reactor Physics, Radiation Shielding, and Computational Methods, had the following membership at the time it reviewed and approved this standard:

T. M. Raby (Chair) *National Institute of Standards and Technology*
A. Weitzberg (Vice Chair), *Individual*

W. H. Bell, *American Institute of Chemical Engineers*
(Alt. R. D. Zimmerman, *American Institute of Chemical Engineers*)
R. E. Carter, *Individual*
D. Cokinos, *Brookhaven National Laboratory*
B. Dodd, *Health Physics Society*
B. K. Grimes, *Individual*
N. Hertel, *Georgia Institute of Technology*
W. A. Holt, *Individual*
W. C. Hopkins, *Individual*
M. A. Hutmaker, *U.S. Department of Energy*
L. I. Kopp, *Individual*
P. M. Madden, *U.S. Nuclear Regulatory Commission*
Alt. A. Adams, *U.S. Nuclear Regulatory Commission*)
J. F. Miller, *James F. Miller Consulting Services*
J. E. Olhoeft, *Individual*
W. J. Richards, *National Institute of Standards and Technology*
T. R. Schmidt, *Sandia National Laboratories*
A. O. Smetana, *Savannah River National Laboratory*
R. Tsukumura, *Aerotest Operations*
S. H. Weiss, *National Institute of Standards and Technology*
Alt. Thomas J. Myers, *National Institute of Standards and Technology*)
W. L. Whittemore, *General Atomics*

Contents	Section	Page
	1 Scope	1
	2 Requirements and recommendations	1
	2.1 Conformance	1
	2.2 Requirements	1
	2.3 Recommendations	2
	3 Standards of documentation	4
	3.1 Shield design approach	4
	3.2 Shield design description	4
	3.3 Methods of analysis	4
	3.4 Description of analyses	4
	3.5 References	4
	3.6 Summary results	4
	4 Terms and definitions	4
	5 Characterization of concrete	6
	5.1 Introduction	6
	5.2 Concrete placement	7
	5.3 Water content	7
	5.4 Heating effects	8
	5.5 Reinforcing steel	8
	5.6 Aggregates	8
	6 Calculation methods	10
	6.1 Introduction	10
	6.2 Point-kernel methods	10
	6.3 Discrete ordinates method	13
	6.4 Monte Carlo method	16
	6.5 Other methods and summary	18
	7 Concrete shielding data	18
	7.1 Introduction	18
	7.2 Gamma-ray attenuation coefficients	19
	7.3 Gamma-ray buildup factors	19
	7.4 Secondary-gamma-ray production	20
	7.5 Neutron cross sections	20
	7.6 Neutron attenuation curves	21
	8 Applications	21
	8.1 Radiation effects	21
	8.2 Minimum water content	22
	8.3 Bulk shielding	23
	8.4 Radiation streaming through penetrations	25
	8.5 Reflection	26
	9 References	27
	Bibliography	32
 Tables		
	Table 1 Typical concrete properties	3
	Table 2 Partial densities of concrete constituents	6

Figures		
Figure 1	Example of oblique penetration short circuit paths	12
Figure 2	P_1 convergence of the fast neutron dose rate in water from a point fission source	15
Figure 3	Comparison of neutron and gamma-ray dose rate through concrete using transport and diffusion theory	17
Figure 4	Example of excess transmission through a void	25
Appendices		
Appendix A	List of codes	33
Appendix B	Shielding data	36
Table B.1	Mass attenuation coefficients, excluding coherent scattering, for concretes described in Table 1 of the standard	37
Table B.2	Mass attenuation coefficients, excluding coherent scattering, for elements comprising ordinary concrete	38
Table B.3	Mass attenuation coefficients, excluding coherent scattering, for elements that may be found in other concrete compositions	39
Table B.4	Mass energy transfer coefficients for concretes described in Table 1 of the standard	40
Table B.5	Mass energy absorption coefficients for concretes described in Table 1 of the standard	41
Table B.6	Taylor coefficients for approximating concrete buildup factors	42
Table B.7	Geometric progression buildup factor coefficients for ordinary concrete (air kerma, 40 mfp)	43
Table B.8	Geometric progression buildup factor coefficients for ordinary concrete (concrete kerma, 40 mfp)	44
Table B.9	Gamma-ray spectra from thermal neutron capture in concrete	45
Table B.10	Neutron constants for concrete	45
Figure B.1	Air kerma buildup factors in concrete, moments method calculations	46
Figure B.2	Concrete kerma buildup factors in concrete, moments method calculations	47
Figure B.3	Air kerma buildup factors in concrete, geometric progression form (energy: 0.03 to 0.2 MeV)	48
Figure B.4	Air kerma buildup factors in concrete, geometric progression form (energy: 0.3 to 2.0 MeV)	49
Figure B.5	Air kerma buildup factors in concrete, geometric progression form (energy: 3.0 to 15.0 MeV)	50
Figure B.6	Concrete kerma buildup factors in concrete, geometric progression form (energy: 0.03 to 0.2 MeV)	51
Figure B.7	Concrete kerma buildup factors in concrete, geometric progression form (energy: 0.3 to 2.0 MeV)	52
Figure B.8	Concrete kerma buildup factors in concrete, geometric progression form (energy: 3.0 to 15.0 MeV)	53
Figure B.9	Comparison of adjoint discrete ordinates and moments method calculations of neutron dose equivalent (rem) from a plane isotropic fission source as a function of concrete thickness, source normalized to one neutron in a forward direction	54

Appendix C	Application data and results	56
Table C.1	Constants for the empirical formulation of the ambient dose $H^*(10 \text{ mm})$ albedo $\alpha_D(E_o, \theta_o, \theta, \phi)$ for neutrons incident on NBS Type 04 concrete	59
Table C.2	Constants for the expressions fitting the Coleman et al. differential and total albedo data for intermediate-energy neutrons incident on reinforced concrete	61
Table C.3	Constants for the empirical formulation of the ambient dose $H^*(10 \text{ mm})$ albedo $\alpha_D(E_o, \theta_o, \theta, \phi)$ for gamma rays incident on NBS Type 04 concrete	62
Table C.4	Parameters for the five-term approximation of the ambient dose equivalent albedo for reflected secondary gamma rays resulting from neutrons incident on ordinary concrete	62
Table C.5	Attenuation factors for monoenergetic beams of gamma rays obliquely incident on slabs of Type 04 ordinary concrete, expressed as the ratio of transmitted to incident air kerma	63
Table C.6	Neutron and secondary-gamma-ray transmission factors for ambient dose $H^*(10)$ (PAR) for neutrons incident on 15-cm-thick slabs of NBS Type 04 ordinary concrete	64
Table C.7	Neutron and secondary-gamma-ray transmission factors for ambient dose $H^*(10)$ (PAR) for neutrons incident on 30-cm-thick slabs of NBS Type 04 ordinary concrete	65
Table C.8	Neutron and secondary-gamma-ray transmission factors for ambient dose $H^*(10)$ (PAR) for neutrons incident on 50-cm-thick slabs of NBS Type 04 ordinary concrete	66
Table C.9	Neutron and secondary-gamma-ray transmission factors for ambient dose $H^*(10)$ (PAR) for neutrons incident on 75-cm-thick slabs of NBS Type 04 ordinary concrete	67
Table C.10	Neutron and secondary-gamma-ray transmission factors for ambient dose $H^*(10)$ (PAR) for neutrons incident on 100-cm-thick slabs of NBS Type 04 ordinary concrete	68
Table C.11	Composition of Hanford ordinary concrete as a function of temperature	69
Table C.12	Compositions of concretes used in measurements	69
Table C.13	ANISN spherical model for pressurized water reactor calculation	70
Table C.14	Material compositions for pressurized water reactor calculation	70
Table C.15	Neutron source distribution for pressurized water reactor calculation	71
Table C.16	Neutron source spectrum for pressurized water reactor calculation	71
Figure C.1	Resonance neutron distribution in ordinary concrete as a function of temperature	72
Figure C.2	Fast neutron distribution in ordinary concrete as a function of temperature	73

Figure C.3	Measured neutron fluxes versus distance in ordinary concrete	74
Figure C.4	Gamma-ray and neutron flux attenuation curves in ordinary concrete	75
Figure C.5	Radiation levels in Bradwell side shield	76
Figure C.6	Dose rates in typical pressurized water reactor shield ...	77
Figure C.7	Gamma-ray dose rates from 4-in. Schedule 80 and Schedule 160 steel pipe, containing airborne or waterborne radioactivity, derived through use of the QADMOD-GP code	78
Figure C.8	Gamma-ray dose rates from 8-in. Schedule 80 and Schedule 160 steel pipe, containing airborne or waterborne radioactivity, derived through use of the QADMOD-GP code	79
Figure C.9	Gamma-ray dose rates from 12-in. Schedule 80 and Schedule 160 steel pipe, containing airborne or waterborne radioactivity, derived through use of the QADMOD-GP code	80
Figure C.10	Gamma-ray dose rates from 16-in. Schedule 80 and Schedule 160 steel pipe, containing airborne or waterborne radioactivity, derived through use of the QADMOD-GP code	81
Figure C.11	Gamma-ray dose rates from 24-in. Schedule 80 and Schedule 160 steel pipe, containing airborne or waterborne radioactivity, derived through use of the QADMOD-GP code	82
Figure C.12	Gamma-ray dose rates from 6-ft outer diameter tank, with 0.25-in. steel wall, containing airborne or waterborne radioactivity, derived through use of the QADMOD-GP code	83
Figure C.13	Penetration types	84
Figure C.14	Geometry for albedos and a sample application	85
Figure C.15	Reflection geometries	86

Nuclear Analysis and Design of Concrete Radiation Shielding for Nuclear Power Plants

1 Scope

This standard contains methods and data needed to calculate the concrete thickness required for radiation shielding in nuclear power plants. Where possible, specific recommendations are made regarding radiation attenuation calculations, shielding design, and standards of documentation. The standard provides guidance to architect-engineers, utilities, and reactor vendors who are responsible for the shielding design of stationary nuclear plants. This standard does not consider sources of radiation other than those associated with nuclear power plants. It also excludes considerations of economic aspects of shielding design.

Concrete is a mixture of materials, the exact proportions of which will differ from application to application. This standard includes a discussion of the nature of concrete, emphasizing those variable aspects of the material that are important to the shield designer. The document discusses methods of analysis and the shielding input data appropriate to each method. Applications of the analytical methods are given, including bulk transport, radiation heating, streaming, and reflection problems.

2 Requirements and recommendations

2.1 Conformance

The word “shall” is used to denote a requirement; the word “should” is used to denote a recommendation; and the word “may” is used to denote permission, neither a requirement nor a recommendation. To conform with this standard, all concrete shield analyses and designs shall be performed in accordance with its requirements, but not necessarily with its recommendations.

2.2 Requirements

2.2.1 Computational methods

Any applicable method may be used by the designer in the analysis of shield effectiveness. The designer shall be aware, however, of any limitations imposed by the method employed. Approximations shall be chosen such that the attenuation afforded by the concrete shield is known to be conservative with respect to the design objective. Conservatism may also be introduced by other means, such as the source strength used or the radiation design dose rate outside the shield; the concrete shield analysis need not necessarily be inherently conservative.

2.2.2 Data

Selection of material composition, density, cross sections, albedos, or other properties shall be made such that calculational results are conservative with respect to the design objectives as measured by attenuation afforded by the shield.

2.2.3 Operational environment

Nuclear heating shall be considered during the determination of the operating temperature and water content of a concrete primary reactor shield and of any other concrete shields that are exposed to an incident energy flux greater than 10^{10} MeV/cm² s and that will operate at a temperature of 65°C or greater.

2.2.4 Penetrations

All penetration configurations in concrete shield walls shall be shown to provide adequate attenuation. This requirement shall be satisfied by one of the following:

- (1) analysis that follows the guidance of Sec. 8.4 of this standard;
- (2) determination that the configuration is similar to one that is functioning properly under comparable conditions in an operating nuclear facility;